



Double Coated Polyester Tapes with Adhesive 830

442F • 442KW • 442W • 442DL

Technical Data

January, 2004

Product Description

These double coated film tapes feature a thin polyester film carrier for dimensional stability and improved handling with ease of die cutting and laminating. 3M™ Adhesive 830 is a firm rubber adhesive system that provides a combination of high shear strength, good temperature performance, good solvent resistance and good quick stick to a wide variety of materials as well as clean removability from many surfaces.

Construction

Products	3M™ Double Coated Tape 442F	3M™ Double Coated Tape 442KW	3M™ Double Coated Tape 442W	3M™ Double Coated Tape 442DL
Adhesive Family:	830 Adhesive Family			
Tape Thickness: (Without liners)	4.0 mils (0.1 mm)			
Tape Thickness: (With liner/liners)	7.0 mils (0.18 mm)	8.5 mils (0.22 mm)	8.5 mils (0.22 mm)	9.5 mils (0.24 mm)
Adhesive Thickness: (Face Side-nonliner side)	1.5 mils (0.038 mm)			
Adhesive Carrier:	1.0 mil (0.025 mm) clear polyester film			
Adhesive Thickness: (Back Side-liner side)	1.5 mils (0.038 mm)			
Release Liner Type: (Primary Liner)	Polyester Film	Polycoated Paper-72 lb. basis weight	Polycoated Paper-72 lb. basis weight	Polycoated Paper-72 lb. basis weight
Release Liner Type: (Second liner-inside of roll)	NA	NA	NA	Polyester Film
Release Liner Color:	Clear	White	White	White/Clear
Liner Thickness: (Primary/secondary)	3.0 mils (0.07 mm)	4.5 mils (0.11 mm)	4.5 mils (0.11 mm)	4.5/1.0 mils (0.11 mm/0.025 mm)

3M™ Double Coated Polyester Tapes with Adhesive 830

442F • 442KW • 442W • 442DL

Typical Physical Properties and Performance Characteristics

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Products	3M™ Double Coated Tape 442F	3M™ Double Coated Tape 442KW	3M™ Double Coated Tape 442W	3M™ Double Coated Tape 442DL
Adhesion to stainless steel ASTM D3330 - 90 degree	Oz/in (N/100 mm)			
- 15 minute RT	53 (58)			
- 72 hour RT	56 (61)			
- 72 hour 158°F	70 (76)			
ASTM D3330 - 180 degree, 2 mil Al foil, 72 hour RT	70 (76)			
Adhesion to other surfaces ASTM D3330 - 90 degree, 2 mil Al foil, 72 hour RT				
ABS	52 (57)			
Polycarbonate	53 (58)			
Polypropylene	40 (44)			
Shear Strength – ASTM D3654 modified - (.5 inch ² sample size)				
1000 grams at 72°F	+10,000 min			
500 grams at 158°F	+10,000 min			
Relative High Temperature Operating Ranges:				
Long Term (days, weeks)	150°F (66°C)			
Short Term (minutes, hours)	180°F (82°C)			

Available Sizes

Available Lengths (Subject to Minimum order requirements)

Products	3M Tape 442F	3M Tape 442KW	3M Tape 442W	3M Tape 442DL
*Standard Sizes:	36 yd (33 m)	36 yd (33 m)	216 yd (198 m)	36 yd (33 m)
Maximum Length				
1/4" to 1/2":	144 yd (132 m)	144 yd (132 m)	NA	NA
1/2" to 54":	360 yd (329 m)	360 yd (329 m)	NA	216 yd (198 m)
Available Widths				
Minimum:	*1/4" (6.35 mm)	1/4" (6.35 mm)	*65" (1651 mm)	*6" (152 mm)
Maximum:	*54" (1372 mm)	54" (1372 mm)	*Call	54" (1372 mm)
Normal Slitting Tolerance:	± 1/32 in. (0.08 mm)	± 1/32 in. (0.08 mm)	± 1/16 in. (0.16 mm)	± 1/32 in. (0.08 mm)
Core Size (ID):	3.0 in. (76.2 mm)	3.0 in. (76.2 mm)	3.0 in. (76.2 mm)	3.0 in. (76.2 mm)

*Questions on minimum shipping quantities and other possible sizes (widths and lengths) should be directed to your local 3M Sales Representative or 3M's Customer Service Department at 1-800-362-3550.

3M™ Double Coated Polyester Tapes with Adhesive 830

442F • 442KW • 442W • 442DL

Features

- Polycoated paper liners and the polyester liners offer moisture stability
- 3M™ Double Coated Polyester Tapes 442F and 442DL (double lined) also offer an extended shelf life of an additional six months.
- Polyester film carrier at its center core which enhances the workability when laminating to various types of surfaces.
- Film also enhances the die cutability of the finished product.
- Provides clean removability from many surfaces.

Application Techniques

Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure helps develop better adhesive contact and improves bond strength.

To obtain optimum adhesion, the bonding surfaces must be clean, dry and well unified. Some typical surface cleaning solvents are isopropyl alcohol or heptane.

Note: Carefully read and follow the manufacturer's precautions and directions for use when working with solvents. These cleaning recommendations may not be in compliance with the rules of certain Air Quality Management Districts in California; consult applicable rules before use.

Ideal tape application temperature range is 70°F to 100°F (21°C to 38°C). Initial tape application to surfaces at temperatures below 50°F (10°C) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

Application Ideas

These tapes are ideal for bonding together a wide variety of similar and dissimilar materials such as rubbers, metals, glass, papers, paints and many plastics. Some application ideas include:

- Splicing of films, foils, papers, fabrics.
- Holding objects where high shear forces are encountered.
- Holding grinding and polishing pads.
- Miscellaneous joining and holding uses.

Application Equipment

Wide web lamination

To apply adhesives in a wide web format, lamination equipment is required to ensure acceptable quality. To learn more about working with pressure-sensitive adhesives please refer to technical bulletin, Lamination Techniques for Converters of Laminating Adhesives (70-0704-1430-8).

For assistance in helping you determine the best dispenser for your application, contact your local 3M sales representative, or the toll free 3M sales assistance number at 1-800-362-3550.

3M™ Double Coated Polyester Tapes with Adhesive 830

442F • 442KW • 442W • 442DL

Storage	Store in original cartons at 70°F (21°C) and 50% relative humidity.
Shelf Life	To obtain best performance, use 3M™ Double Coated Polyester Tapes 442F and 442DL within 18 months from date of manufacture, and 3M™ Double Coated Polyester Tapes 442KW and 442W within 12 months from date of manufacture. Shelf life may be extended by keeping tape poly bagged and refrigerated at or below 50°F (10°C).
Certification/ Recognition	MSDS: 3M has not prepared a MSDS for these products which are not subject to the MSDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R. 1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the 3M directions for use, these products should not present a health and safety hazard. However, use or processing of these products in a manner not in accordance with the directions for use may affect their performance and present potential health and safety hazards. TSCA: These products are defined as articles under the Toxic Substances Control Act and therefore, are exempt from inventory listing requirements.
For Additional Information	To request additional product information or to arrange for sales assistance, call toll free 1-800-362-3550 or visit www.3M.com/industrialtape . Address correspondence to: 3M Industrial Adhesives and Tapes Division, Building 21-1W-10, 900 Bush Avenue, St. Paul, MN 55144-1000. Our fax number is 651-778-4244. In Canada, phone: 1-800-364-3577. In Puerto Rico, phone: 1-787-750-3000. In Mexico, phone: 52-70-04-00.
Product Use	All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.
Warranty and Limited Remedy	Unless stated otherwise in 3M's product literature, packaging inserts or product packaging for individual products, 3M warrants that each 3M product meets the applicable specifications at the time 3M ships the product. Individual products may have additional or different warranties as stated on product literature, package inserts or product packages. 3M MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. If the 3M product is defective within the warranty period, your exclusive remedy and 3M's and seller's sole obligation will be, at 3M's option, to replace the product or refund the purchase price.
Limitation of Liability	Except where prohibited by law, 3M and seller will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

ISO 9001

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.



Industrial Business Industrial Adhesives and Tapes Division

3M Center, Building 21-1W-10, 900 Bush Avenue
St. Paul, MN 55144-1000



Recycled Paper
40% pre-consumer
10% post-consumer

Printed in U.S.A.
©3M 2004 70-0709-3912-2 (1/04)