



Double Coated Tape

GI612(B)

Technical Data

Apr. 2011

Product Description	GI612(B): 3M™ Double Coated PET Tape with a thin polyester film for dimensional stability and improved handling with ease of die cutting and laminating. The high tack adhesive provides high initial adhesion and good shear holding power to a variety of surfaces.
----------------------------	--

Construction	GI612(B)
Faceside ¹ Adhesive Type/Thickness	Acrylate /0.0022" (0.056mm)
Backside ² Adhesive Type/Thickness	Acrylate /0.0022" (0.056mm)
Liner Color , Type, Print	White PCK liner with red 3M logo
Liner Caliper	0.005" (0.13mm)
Carrier Type	Clear PET ³ /0.0005" (0.013mm)

Note 1: Faceside adhesive is on the interior of the roll, exposed when unwound.

Note 2: Backside adhesive is on the exterior of the roll, exposed when liner is removed.

Note 3: PET (Polyester)

3M™ Double Coated Tape GI612(B)

Typical Physical Properties and Performance Characteristics

Note : The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Product Number	GI612(B)
Adhesion to stainless steel	Oz/in
ASTM D3330-180 degree, 2 mil PET	(N/100mm)
- 15 minute RT	85 (93)
- 72 hour RT	93(102)
Adhesion to PET	
ASTM D3330 –180 degree, 2mil PET	
- 15 minute RT	75 (83)
Adhesion to other substrates	
ASTM D3330 – 180 degree, 2 mil PET, 15 minutes RT	
ABS	70 (76)
Polycarbonate	82 (91)
Shear Strength – ASTM D3654 (1 inch ² sample size, minutes to failure)	
500 grams at 72° F (22°C)	5000 minutes
Relative solvent resistance	Medium-Low
UV Resistance	Medium
Relative High Temperature	
Operating Ranges:	
Long Term (days, weeks)	80°C
Short Term (minutes, hours)	200°C
Shelf Life of Tape in Roll Form	24 months from date of manufacture when stored in original cartons at 70° F (21 °C) and 50% relative humidity.

3M™ Double Coated Tape GI612(B)

Application Techniques	Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure helps develop better adhesive contact and improves bond strength. To obtain optimum adhesion, the bonding surfaces must be clean, dry and well unified. Some typical surface cleaning solvents are isopropyl alcohol or heptane. Note: Carefully read and follow the manufacturer's precautions and directions for use when working with solvents. Ideal tape application temperature range is 70°F to 100°F (21°C to 38°C). Initial tape application to surfaces at temperatures below 50°F (10°C) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.
General Information	All tapes have a film carrier, which can add dimensional stability to foams and other substrates. The carrier also provides easier handling during slitting and die-cutting.
Features	3M™ Adhesive is a medium-firm acrylic adhesive system featuring both high initial adhesion and good high temperature holding power.
Application Ideas	• Medical/non-medical diagnostic test strips • Plastic film lamination/bonding • Splicing • Foam lamination
Application Equipment	To apply adhesives in a wide web format, lamination equipment is required to ensure acceptable quality. To learn more about working with pressure-sensitive adhesives please refer to technical bulletin, Lamination Techniques for Converters of Laminating Adhesives. For additional dispenser information, contact your local 3M sales representative.

3M™ Double Coated Tape GI612(B)

Certification/ Recognition	MSDS: 3M has not prepared a MSDS for the products which are not subject to the MSDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R.
---------------------------------------	---

TSCA: The product are defined as articles under the Toxic Substances Control Act and therefore, are exempt from inventory listing requirements.

Important Notice	3M MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's method of application. Please remember that many factors can affect the use and performance of a 3M product in a particular application. The materials to be bonded with the product, the surface preparation of those materials, the product selected for use, the conditions in which the product is used, and the time and environmental conditions in which the product is expected to perform are among the many factors that can affect the use and performance of a 3M product. Given the variety of factors that can affect the use and performance of a 3M product, some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.
-----------------------------	--

Limitation of Remedies and Liability	If the 3M product is proved to be defective, The exclusive remedy, at 3M'S option, shall be to refund the purchase price of or to repair or rplace the defective 3M product. 3M shall not otherwise be liable for loss or damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including, but not limited to, contract, negligence, warranty, or strict liability.
---	--

ISO 9002

This Engineered Adhesives Division product was manufactured under a 3M quality system registered to ISO 9002 standards.

3M

3M Maxdo, Xingyi Road 8
Shanghai, PRC.

• **3M** 2011