



Adhesive Transfer Tapes with Adhesive 300MP

9772WL • 9773WL • 9774WL • 9775WL

Technical Data

June, 2008

Description 3M™ Adhesive Transfer Tapes 9772WL, 9773WL, 9774WL and 9775WL with 3M™ Adhesive 300MP are suitable for bonding to most surfaces. The acrylic adhesive provides an excellent bond to various fabricated foams, fabrics, substrates, and has good shear strength at elevated temperatures. These tapes also meet the highly variable needs of most gasket fabricators.

Construction	Product	3M Tape 9772WL	3M Tape 9773WL	3M Tape 9774WL	3M Tape 9775WL
	Adhesive:	2.0 mils (51 microns) 300MP Hi-Strength Acrylic Adhesive	3.0 mils (76 microns) 300MP Hi-Strength Acrylic Adhesive	4.0 mils (102 microns) 300MP Hi-Strength Acrylic Adhesive	5.0 mils (127 microns) 300MP Hi-Strength Acrylic Adhesive
	Liner:	7.0 mils (178 microns) 96# White Polycoated Kraft Paper	7.0 mils (178 microns) 96# White Polycoated Kraft Paper	7.0 mils (178 microns) 96# White Polycoated Kraft Paper	7.0 mils (178 microns) 96# White Polycoated Kraft Paper

Typical Physical Properties and Performance Characteristics

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Adhesion: ASTM D3330 (modified) 90° Peel, 12"/minute (305 mm/minute),
2 mil aluminum foil to various surfaces.

Surface	72 Hour Dwell		72 Hour Dwell @ 158°F (70°C)		72 Hour Dwell @ 100°F (38°C)/100% RH	
	Oz./ln.	N/100 mm	Oz./ln.	N/100 mm	Oz./ln.	N/100 mm
Stainless Steel						
3M Tape 9772WL	58	64	93	103	65	72
3M Tape 9773WL	65	72	122	136	90	100
3M Tape 9774WL	75	83	134	149	106	118
3M Tape 9775WL	88	98	177	197	110	122
ABS (High Surface Energy Plastic)						
3M Tape 9772WL	47	52	31	34	36	40
3M Tape 9773WL	59	66	45	50	45	50
3M Tape 9774WL	65	72	48	53	53	59
3M Tape 9775WL	72	80	49	54	55	61

3M™ Adhesive Transfer Tapes with Adhesive 300MP

9772WL • 9773WL • 9774WL • 9775WL

Typical Physical Properties and Performance Characteristics (continued)

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Surface	72 Hour Dwell		72 Hour Dwell @ 158°F (70°C)		72 Hour Dwell @ 100°F (38°C)/100% RH	
	Oz./In.	N/100 mm	Oz./In.	N/100 mm	Oz./In.	N/100 mm
Polypropylene (Low Surface Energy Plastic)						
3M™ Adhesive Transfer						
Tape 9772WL	26	29	31	34	57	63
Tape 9773WL	33	37	37	41	61	68
Tape 9774WL	36	40	40	44	64	71
Tape 9775WL	46	51	44	49	65	72

Environmental Performance

The bond strength of the adhesive increases as a function of time and temperature.

Temperature Resistance: Short term: 250 (121°C).

Humidity Resistance: No adverse effect on the bond after exposure to 100% relative humidity at 100 (38°C).

U.V. Resistance: Adhesive is resistant to oxidation and ozone when exposed to air or ultraviolet light.

Typical Static Shear Performance

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Shear Adhesion: (ASTM D3654, 1" x 1" Overlap with one hour dwell).

Surface	Minutes to Fail	
Stainless Steel	1000 grams at room temperature	
	3M Tape 9772WL	10,000
	3M Tape 9773WL	10,000
	3M Tape 9774WL	10,000
	3M Tape 9775WL	10,000
	250 grams @ 158°F (70°C) high temperature shears	
	3M Tape 9772WL	10,000
	3M Tape 9773WL	10,000
	3M Tape 9774WL	10,000
	3M Tape 9775WL	10,000

Storage

Store at room temperature conditions of 72°F (22°C) and 50% relative humidity.

Shelf Life

Product retains its performance properties for two years from date of manufacture.

3M™ Adhesive Transfer Tapes with Adhesive 300MP

9772WL • 9773WL • 9774WL • 9775WL

Product Use

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

Warranty and Limited Remedy

Unless stated otherwise in 3M's product literature, packaging inserts or product packaging for individual products, 3M warrants that each 3M product meets the applicable specifications at the time 3M ships the product. Individual products may have additional or different warranties as stated on product literature, package inserts or product packages. 3M MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. If the 3M product is defective within the warranty period, your exclusive remedy and 3M's and seller's sole obligation will be, at 3M's option, to replace the product or refund the purchase price.

Limitation of Liability

Except where prohibited by law, 3M and seller will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

ISO 9001:2000

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2000 standards.



Industrial Adhesives and Tapes Division Converter Markets

3M Center, Building 21-1W-10, 900 Bush Avenue
St. Paul, MN 55144-1000
800-223-7427 • 651-778-4244 (fax)
www.3M.com/converter



Recycled Paper
40% pre-consumer
10% post-consumer

3M is a trademark of 3M Company.
Printed in U.S.A.
©3M 2008 70-0713-4522-0 (6/08)