



HYSOL[®] ES6005[™]

August 2005

PRODUCT DESCRIPTION

HYSOL[®] ES6005[™] provides the following product characteristics:

Technology	Epoxy
Appearance (Part A)	Black
Appearance (Part B)	Amber - green
Components	Two component - requires mixing
Mix Ratio, by volume - Part A: Part B	2 : 1
Mix Ratio, by weight - Part A: Part B	100 : 29.5
Cure	Room temperature cure
Application	Potting and Encapsulating

HYSOL[®] ES6005[™] is a resilient, low cost, fast gelling, potting compound. Designed for easy 2 to 1 meter-mix-dispense machinery and low abrasion. This material is ideal for potting and encapsulating high volume parts.

UL Classification

Classified by Underwriters Laboratories Inc.[®] UL 1446 as a potting compound with and without varnish up to a temperature of 180 °C. UL recognized 94 HB Flame Retardent to 1.5 mm thickness.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Part A Properties

Density @ 25 °C, g/cm ³	1.63
Viscosity @ 25 °C, mPa·s (cP)	11,000

Part B Properties

Density @ 25 °C, g/cm ³	0.97
Viscosity @ 25 °C, mPa·s (cP)	170

Mixed Properties

Density @ 25 °C, g/cm ³	1.41
Viscosity @ 25 °C, mPa·s (cP)	1,500
Working Life @ 25 °C, minutes:	
400 g mass	10
Gel Time @ 25 °C, minutes:	
400 g mass	25

TYPICAL CURING PERFORMANCE

Recommended Curing Conditions

16 hours @ 25 °C (Recommended cure)
2 hours @ 66 °C (Alternate cure)

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties:

Glass Transition Temperature, ASTM D 3418, °C	62
Coefficient of Thermal Expansion, ASTM D 3148, K ⁻¹ :	
Pre Tg (alpha 1)	65×10 ⁻⁶
Post Tg (alpha 2)	180×10 ⁻⁶
Coefficient of Thermal Conductivity, ISO 8302, W/(m·K)	0.288
Shore Hardness, ISO 868, Durometer D	70

Water Absorption, ISO 62, %:

24 hours in water @ 25 °C	0.3
Tensile Strength, ASTM D 638	N/mm ² 12.4
	(psi) (1,800)

Electrical Properties:

Volume Resistivity, IEC 60093, Ω·cm	4.9×10 ¹³
Surface Resistivity, IEC 60093, Ω	5.4×10 ¹⁴
Arc Resistance, ASTM D495, seconds	87
Dielectric Breakdown Strength IEC 60243-1, kV/mm	38
Dielectric Constant / Dissipation Factor, IEC 60250:	
100 Hz	5.2 / 0.04
1 kHz	5.0 / 0.03
100 kHz	4.5 / 0.03

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Liquid Storage - Liquids should be stored at 23°C or below, in closed containers. If stored below 23°C, the material MUST be allowed to come to room temperature, in the sealed container, to avoid moisture contamination.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

(°C x 1.8) + 32 = °F
kV/mm x 25.4 = V/mil
mm / 25.4 = inches
N x 0.225 = lb
N/mm x 5.71 = lb/in
N/mm ² x 145 = psi
MPa x 145 = psi
N·m x 8.851 = lb·in
N·m x 0.738 = lb·ft
N·mm x 0.142 = oz·in
mPa·s = cP

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. [®] denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1.0