



HYSOL ES1904

May 2012

PRODUCT DESCRIPTION

HYSOL ES1904 provides the following product characteristics:

Technology	Epoxy
Appearance (cured)	Opaque
Components	Two component - requires mixing
Mix Ratio, by volume - Part A: Part B	2 : 1
Mixing Ratio, by weight Component A: Component B	100 : 46
Cure	Room temperature cure
Application	Potting and Encapsulating

HYSOL ES1904 is an opaque, medium-viscosity epoxy resin formulation recommended for small potting and laminating applications, excellent structural, mechanical and electrical properties are required. This two-part adhesive exhibits good wetting, cures at room temperature and develops strong, low shrinkage bonds to most materials including optical fibers, glass ceramics, most metals. It has excellent dimensional stability over a wide temperature range. This product is typically used in applications with an operating range of -60 °C to +125 °C.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Part A Properties

Density, @ 25 °C, g/cm ³	1.19
Viscosity @ 25 °C, cP	25,000

Part B Properties

Density, @ 25 °C, g/cm ³	1.09
Viscosity @ 25 °C, cP	50,000

Mixed Properties

Pot Life @ 25 °C, minutes:	
100 g mass	8 to 10
Gel Time @ 25 °C, minutes:	
100 g mass	9 to 14
Specific Gravity	1.15
Viscosity @ 25 °C, cP	40,000

TYPICAL CURING PERFORMANCE

Recommended Curing Conditions

- 12 to 24 hours @ 25 °C (Recommended cure)
- 2 hours @ 65 °C (Alternate cure)
- 1 hour @ 100 °C (Alternate cure)

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties:

Glass Transition Temperature, °C	80
Coefficient of Thermal Expansion, ppm/°C:	
Pre Tg (Alpha 1)	68
Post Tg (Alpha 2)	190
Shore Hardness, Durometer D	90

24 Hour Water Moisture Absorption, %	0.3
Tensile Elongation, %	6
Tensile Strength, psi	9,900
Compressive Strength, psi	19,000
Flexural Strength, psi	14,500

Electrical Properties:

Dielectric Strength, volts/mil	1,640
Volume Resistivity, ohm-cm	3×10 ¹⁶
Surface Resistivity, ohms @ 25°C	3×10 ¹⁶
Dielectric Constant / Dissipation Factor @ 25°C:	
1 kHz	4.0 / 0.009

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Note: Before using this product please purge approximately 30 ml. of material prior to application. Discard purged material in accordance with the Material Safety Data Sheet. A video instruction is available upon request.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 20 °C to 30 °C. Storage below 20 °C or greater than 30 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

(°C x 1.8) + 32 = °F
kV/mm x 25.4 = V/mil
mm / 25.4 = inches
N x 0.225 = lb
N/mm x 5.71 = lb/in
N/mm ² x 145 = psi
MPa x 145 = psi
N·m x 8.851 = lb·in
N·m x 0.738 = lb·ft
N·mm x 0.142 = oz·in
mPa·s = cP



Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation and its affiliates ("Henkel") specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel products. Henkel specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

All trademarks in this document are trademarks and/or registered trademarks of Henkel in the US and elsewhere.

Reference 0.0