

LOCTITE STYCAST 1266J Parts AB

August 2013

PRODUCT DESCRIPTION

LOCTITE STYCAST 1266J Parts AB provides the following product characteristics:

Technology	Epoxy
Technology (Part B)	Amine
Appearance, Resin (Component A)	Clear amber liquid
Appearance, Hardener (Component B)	Clear yellow liquid
Components	Two component - requires mixing
Mixing Ratio, by weight Component A: Component B	100 : 28
Mixing Ratio, by volume Component A: Component B	100 : 33
Product Benefits	• Optical clarity • Low viscosity • High impact strength • Room temperature cure capability • Good moisture resistance • Good electrical properties
Cure	Room Temperature or Heat Cure
Application	Assembly
Operating Temperature	-65 to 105°C
Substrates	Metals, Glass, Plastics

LOCTITE STYCAST 1266J Parts AB is a low viscosity material, making it suitable for impregnating applications with small tolerances. It is designed for use to readily impregnate windings, bond lenses and sheets for good visibility or for display embedments.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Part A Properties

Brookfield Viscosity , ASTM D2393, mPa·s (cP)	8,500
Density, ASTM D792, g/cm ³	1.16
Flash Point - See MSDS	

Part B Properties

Brookfield Viscosity ASTM D2393, mPa·s (cP)	35
Density, ASTM D792, g/cm ³	1.0
Flash Point - See MSDS	

Mixed Properties

Density, ASTM D792, g/cm ³	1.12
Brookfield Viscosity , ASTM D2393, mPa·s (cP)	650
Work Life , 100 gram mass @ 25 °C, minutes	30
Shelf Life @ 25°C (from date of manufacture), days	365
Flash Point - See MSDS	

TYPICAL CURING PERFORMANCE

Cure Schedule

8 to 16 hours @ 25°C
1 to 2 hours @ 65°C

Cure at any one of the recommended cure schedules.

For optimum performance, follow the initial cure with a post cure of 2 hours at 100 °C.

Alternate cure schedules may also be possible. Contact your Henkel representative for further information.

This product generates moderate heat during cure. No adverse exotherm effects are obtained when cured at 65°C in masses up to approximately 100 grams.

Applications requiring more than 100 grams of material should be cured at the lowest recommended temperature to prevent the possibility of adverse exotherm effects.

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL AS MIXED

Physical Properties

Hardness, Shore D, ASTM D2240	75
-------------------------------	----

Electrical Properties

Dielectric Strength , ASTM D149, kV/mm	15.7
Dielectric Constant / Dissipation Factor, ASTM D150: @ 60Hz	3.0/0.02
Volume Resistivity @ 25 °C, ASTM D257, ohm-cm	1×10 ¹⁵

TYPICAL PERFORMANCE OF CURED MATERIAL AS MIXED

Miscellaneous

Flexural Strength, ASTM D790	N/mm ² 138 (psi) (20,000)
Compressive Strength , ASTM-D695	N/mm ² 69 (psi) (10,000)
Tensile Strength , ASTM D412	N/mm ² 41 (psi) (6,000)

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

DIRECTIONS FOR USE

1. Complete cleaning of the substrates should be performed to remove contamination such as oxide layers, dust, moisture, salt and oils which can cause poor adhesion or corrosion in a bonded part.
2. Accurately weigh resin and hardener into a clean container in the recommended ratio. Weighing apparatus having an accuracy in proportion to the amounts being weighed should be used.
3. Blend components by hand, using a kneading motion, for 2 to 3 minutes and scrape the bottom and sides of the mixing container frequently to produce a uniform mixture.
4. If possible, power mix for an additional 2 to 3 minutes. Avoid high mixing speeds which could entrap excessive amounts of air or cause overheating of the mixture resulting in reduced working life.
5. To ensure a void-free embedment, vacuum deairing should be used to remove any entrapped air introduced during the mixing operation.
6. Vacuum deair mixture at 1 to 5 mm mercury. The foam will rise several times the liquid height and then subside.
7. Continue vacuum deairing until most of the bubbling has ceased. This usually takes 3 to 10 minutes.
8. Pour mixture into cavity or mold.
9. Gentle warming of the mold or assembly reduces the viscosity. This improves the flow of the material into the unit having intricate shapes or tightly packed coils or components.
10. Further vacuum deairing in the mold may be required for critical applications.
11. Certain resins and hardeners are prone to crystallization. If crystallization does occur, warm the contents of the shipping container to 50 to 60°C until all crystals have dissolved. Shipping container must be loosely covered during the warming stage to prevent any pressure build-up.
12. Allow contents to cool to room temperature before continuing.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Storage

Store in original, tightly covered containers in clean, dry areas. Storage information may be indicated on the product container labeling.

Optimal Storage: 25°C. Storage below 25°C or greater than 25°C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} = \text{N/mm}^2$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.0