

PRODUCT DESCRIPTION

LOCTITE® PE 3141 Epoxy Resin is a resin formulated to offer improved long term performance at higher temperatures when mixed with LOCTITE® PE 3163 Epoxy Hardener. This mixture forms a resilient, long work time potting compound with an easy mix ratio and good adhesion to thermoplastics.

PROPERTIES OF UNCURED MATERIAL (Resin)

	Typical Value
Chemical Type	Epoxy resin
Appearance	Black
Viscosity, Spindle #7 @ 20 RPM, 25°C, cP	80,000
Specific Gravity	1.61

PROPERTIES OF UNCURED MATERIAL (Hardener)

	Typical Value
Chemical Type	Epoxy hardener
Appearance (mixed)	Amber (black)
Viscosity, Spindle #2 @ 20 RPM, 25°C, cP	450
specific Gravity	0.96

PROPERTIES OF CURED MATERIAL

	Typical Value
Vol. Mix Ratio, Resin:Hardener	2 to 1
Weight Mix Ratio, Resin:Hardener	100:30
Mixed Specific Gravity	1.40
Mixed Viscosity, Spindle 5 @ 20 rpm 25°C, cP	4,000
Work Time, 200g (25°C)	30-45 min
Gel Time, 200g (25°C)	60-80 min
Regular Cure Schedule (25°C)	24 hr
Alternate Cure Schedule (66°C)	2 hours
CTE below Tg, ASTM E831 (mm/mm°C)	52.6 E-06
Tg, ASTM D3418-82, °C	38
CTE above Tg, ASTM E831 (mm/mm°C)	138 E-06
Hardness, ASTM D2240, Shore D	80

Electrical Properties

Dielectric Constant, ASTM D150	
0.1 kHz	3.58
1.0 kHz	3.52
10 kHz	3.46
100 kHz	3.39
Dissipation Factor, ASTM D150	
0.1 kHz	0.01
1.0 kHz	0.01
10 kHz	0.01
100 kHz	0.02
Insulation, ASTM D257, ohms	1.23 E14
Volume Resistivity, ASTM D257, Ω.cm	7.41 E15
Dielectric Strength, ASTM D149, V/mil	385

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected for use with chlorine or other strong oxidizing materials. For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

Storage

Product shall be ideally stored in a cool, dry location in unopened containers at a temperature between 8°C to 28°C (46°F to 82°F) unless otherwise labeled. Optimal storage is at 0°C (32°F) or less. To prevent contamination of unused product, do not return any material to its original container. For further specific shelf life information, contact your local Technical Service Center.

Data Ranges

The data contained herein may be reported as a typical value and/or range. Values are based on actual test data and are verified on a periodic basis.

Properties of Uncured Material

	Specific Gravity	Viscosity, cP@ 25°C	Color	Mixed Color
LOCTITE PE 3141 Epoxy Resin	1.61	80,000	Black	
LOCTITE PE 3160 Epoxy Hardener	1.00	180	Clear	Black
LOCTITE PE 3162 Epoxy Hardener	0.99	120	Clear	Black
LOCTITE PE 3163 Epoxy Hardener	0.96	450	Amber	Black
LOCTITE PE 3164 Epoxy Hardener	0.97	105	Amber	Black
LOCTITE PE 3165 Epoxy Hardener	0.96	55	Clear	Black

Curing Properties of the Systems

(All Properties in Conjunction with HYSOL 3141 Epoxy Resin)

Hardener	Vol. Mix Ratio <i>Resin:Hardener</i>	Weight Mix Ratio <i>Resin:Hardener</i>	Mixed Specific Gravity	Mixed Viscosity, cP @ 25°C	Work Time 200g (25°C) unless otherwise noted	Gel Time 200g (25°C, 77°F) unless otherwise noted	Regular Cure Schedule (25°C, 77°F)	Alternate Cure Schedule (66°C, 150°F)
LOCTITE PE 3160 Epoxy Hardener	2.5 to 1	4 : 1	1.44	7,000	90 – 120min/400g	2.5 to 3.5 hr/400 gm	24 hr	4 hours
LOCTITE PE 3162 Epoxy Hardener	3 to 1	100 : 19.8	1.46	5,000	5min	10 - 15 min	24 hr	2 hours
LOCTITE PE 3163 Epoxy Hardener	2 to 1	100: 30	1.40	4,000	30 – 45 min	60 – 80 min	24 hr	2 hours
LOCTITE PE 3164 Epoxy Hardener	2 to 1	100 : 31.5	1.40	6,000	10min/400g	20 – 25 min	24 hr	2 hours
LOCTITE PE 3165 Epoxy Hardener	6.5 to 1	100 : 9	1.40	13,000	35 – 40 min	65 – 75 min	24 hr (25°C) & 4 hr (93°C)	-----

Cured Properties of the System

Hardener	CTE below Tg (mm/mm°C)	Tg, °C	CTE above Tg (mm/mm°C)	Hardness Shore D
LOCTITE PE 3160 Epoxy Hardener	60.7 E-06	43	160 E-06	85
LOCTITE PE 3162 Epoxy Hardener	39.7 E-06	75	135 E-06	90
LOCTITE PE 3163 Epoxy Hardener	52.6 E-06	38	138 E-06	80
LOCTITE PE 3164 Epoxy Hardener	49.2 E-06	31	111 E-06	85
LOCTITE PE 3165 Epoxy Hardener	35.0 E -06	104	115 E-05	85

Dielectric Constant				
Hardener	Frequency			
	0.1 KHz	1.0 KHz	10 KHz	100 KHz
LOCTITE PE 3160 Epoxy Hardener	4.30	4.22	4.14	4.03
LOCTITE PE 3162 Epoxy Hardener	3.91	3.88	3.84	3.79
LOCTITE PE 3163 Epoxy Hardener	3.58	3.52	3.46	3.39
LOCTITE PE 3164 Epoxy Hardener	4.11	3.97	3.87	3.77
LOCTITE PE 3165 Epoxy Hardener	4.28	4.18	4.06	3.92

Dissipation Factor				
Hardener	Frequency			
	0.1 KHz	1.0 KHz	10 KHz	100 KHz
LOCTITE PE 3160 Epoxy Hardener	0.01	0.01	0.02	0.02
LOCTITE PE 3162 Epoxy Hardener	0.01	0.01	0.01	0.01
LOCTITE PE 3163 Epoxy Hardener	0.01	0.01	0.01	0.02
LOCTITE PE 3164 Epoxy Hardener	0.02	0.02	0.02	0.02
LOCTITE PE 3165 Epoxy Hardener	0.01	0.02	0.02	0.02

Hardener	Insulation Resistance, ohms	Volume Resistivity, Ω.cm	Dielectric Strength, Volts/mil
LOCTITE PE 3160 Epoxy Hardener	5.72 E13	4.03 E15	375
LOCTITE PE 3162 Epoxy Hardener	4.09 E13	2.61 E15	335
LOCTITE PE 3163 Epoxy Hardener	1.23 E14	7.41 E15	385
LOCTITE PE 3164 Epoxy Hardener	4.57 E13	2.98 E15	395
LOCTITE PE 3165 Epoxy Hardener	2.15 E13	1.37 E15	365

Note

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.