

LOCTITE STYCAST E 1470

October 2014

PRODUCT DESCRIPTION

LOCTITE STYCAST E 1470 provides the following product characteristics:

Technology	Epoxy
Appearance	Off-white
Components	One-component
Product Benefits	• Thermosetting • B-Stageable • Controlled particle size • Controlled rheology • Sag resistant • Excellent adhesion • Non-conductive
Cure	Heat Cure
Application	Assembly
Surfaces	LCP, Silicon, Metals, Aluminum and Plastics
Typical Package Application	Component attach and Lid seal

LOCTITE STYCAST E 1470 adhesive is designed for component attach and lid seal applications. LOCTITE STYCAST E 1470 can be applied by syringe dispense and cured in conventional batch oven or continuous IR convection oven at low temperatures.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity, AR 1000, mPa·s (cP)	12,000
Shear Thinning Index (Rheometer)	2.1
Shelf Life:	
@ -20°C (wet), days	91
Pot Life:	
@ 25°C (wet), days	7
@ 25°C (dry), days	30
Flash Point - See SDS	

TYPICAL CURING PERFORMANCE**Recommended B-Stage Condition**

45 minutes @ 100°C - Batch

Cure Schedule

5 minutes @ 180°C

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL**Physical Properties :**

Glass Transition Temperature, DMA, °C	85
Thermal Conductivity, W/(m·K)	0.2
Water Absorption, %:	
85°C/85 RH	2
Thermal Decomposition TGA, °C	300

TYPICAL PERFORMANCE OF CURED MATERIAL**Lap Shear Strength :**

LCP	N/mm ²	13
	(psi)	(1,900)
Gold	N/mm ²	17
	(psi)	(2,500)
Ceramic	N/mm ²	16.5
	(psi)	(2,400)

PERFORMANCE AND RELIABILITY DATA

Gross Leak Results	Pass
1,000 hours, 85°C/85 RH, 150°C	

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

THAWING:

1. Allow material to reach room temperature before use.

DIRECTIONS FOR USE

1. LOCTITE STYCAST E 1470 is sag resistant and can be dispensed on vertical surfaces like the edge of a lid.
2. B-stage using a conventional batch oven, then cure in a batch oven or continuous IR convection oven.
3. LOCTITE STYCAST E 1470 can be dispensed on the underside of a lid or component and dried to tack-free. In this state, the pre-applied adhesive can be stored and/or shipped to another location for attachment.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : -20 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} = \text{N/mm}^2$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as

well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.2