

Ablestik

ABLEBOND 975-2H

July 2010

PRODUCT DESCRIPTION

ABLEBOND 975-2H provides the following product characteristics:

Technology	Epoxy
Appearance	Blue
Cure	Heat cure and Snap Cure
Application	Die attach
Product Benefits	• Electrically Insulating
Filler Type	Silica
Operating Temperature	-55 to 150°C

ABLEBOND 975-2H adhesive is a high thixotropic index version of ABLEBOND 975-1 adhesive.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity @ °C, mPa·s (cP) 100,000

Work Life @ 25°C, hours 24

Shelf Life @ -40°C (from date of manufacture), year 1

Flash Point - See MSDS

TYPICAL CURING PERFORMANCE

Snap Cure Condition

20 seconds @ 200°C

Recommended Curing Conditions

1 hour @ 80°C

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties:

Coefficient of Thermal Expansion :	
Below Tg (-55 to 118°C), ppm/°C:	26
Above Tg (118 to 150°C), ppm/°C:	13
Glass Transition Temperature, °C	118
Extractable Ionic Content, ppm:	
Chloride (Cl-)	<10
Sodium (Na+)	<10
Potassium (K+)	<5
Water Extract Conductivity, mmhos/cm	25
Thermal Conductivity @ 121°C, BTU/ft·hr·°F	0.31
Weight Loss @ 250°C, %	0.17

Electrical Properties:

Volume Resistivity, ohms-cm	6.35×10 ¹²
Dielectric Constant @ 1KHz	3.68
Dissipation Factor @ 1KHz	0.005

TYPICAL PERFORMANCE OF CURED MATERIAL

Die Shear Strength 70mil² (1.8 mil²) die:

@ 25°C:	
N/mm ²	61.93
kg/cm ²	630
@ 350°C:	
N/mm ²	2.76
kg/cm ²	28

Lap Shear Strength Al to Al @ 25°C:

N/mm ²	14.48
kg/cm ²	150

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

THAWING:

1. Allow container to reach room temperature before use.
2. After removing from the freezer, set the syringes to stand vertically while thawing.
3. DO NOT open the container before contents reach 25°C temperature. Any moisture that collects on the thawed container should be removed prior to opening the container.
4. DO NOT re-freeze. Once thawed to 25°C, the adhesive should not be re-frozen.

DIRECTIONS FOR USE

1. Thawed adhesive should be immediately placed on dispense equipment for use.
2. If the adhesive is transferred to a final dispensing reservoir, care must be exercised to avoid entrapment of contaminants and/or air into the adhesive.
3. Adhesive must be completely used within the product's recommended work life.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: -40 °C. Storage below minus (-)40 °C or greater than minus (-)40 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all marks used above on this data sheet are trademarks and/or registered trademarks of Henkel and/or its affiliates in Germany and elsewhere.

Reference 0.0