

ELASTOSIL® Solar 2202 A/B

Silicone Gel

Characteristics

ELASTOSIL® Solar 2202 is a pourable, addition-curing, RTV-2 silicone rubber that vulcanizes at room temperature to yield a very soft silicone gel.

Special characteristics

- Two-part system, 1:1 mixing ratio
- Low viscosity
- Rapid heat cure
- Very low hardness (silicone gel)
- Crystal clear vulcanisate
- Pronounced inherent tack
- Long-term stability against weathering, moisture and UV radiation
- Electrically insulating

Product data (uncured)

Property	Test method	Unit	Value	
Component			A	B
Color			Transparent	Transparent
Viscosity at 23 °C	ISO 3219	[mPa s]	1,000	1,000
Density at 23 °C		[g/cm³]	0.97	0.97

Product data (catalyzed A+B)

Property	Test method	Unit	Value
Platinum-catalyst in component			B
Mixing ratio		A : B	1 : 1
Viscosity of mix	ISO 3219	[mPa s]	1,000
Pot life at 23 °C		[h]	2.5

Product data (cured)

Property	Test method	Unit	Value
Color			Crystal clear
Density at 23 °C	ISO 2781	[g/cm³]	0.97
Penetration (150 g hollow cone)	DIN ISO 2137	[mm/10]	300
Dielectric strength	IEC 243	[kV/mm]	23
Volume resistivity	IEC 93	[Ωcm]	10 ¹⁶
Dielectric constant	VDE 0303 T4 / 50 Hz	[ε _r]	2.7
Dissipation factor	VDE 0303 T4 / 50 Hz	[tan δ]	10 × 10 ⁻⁴
Tracking resistance	DIN IEC 112	[CTI]	> 600
Surface resistivity	DIN IEC 93	[Ω]	10 ¹⁴
Refractive index	n _D ²⁵		1.404

Cured for 30 min at 150 °C in circulating air oven.

All figures given above are only intended as a guide and should not be used in preparing specifications.

Application

- Multi-purpose potting agent for the PV industry
- Encapsulation of electronic components of e.g. the junction box or power inverters
- Encapsulation of solar cells

Processing

Caution

Only A and B components with the **same batch number** may be processed together!

Surface preparation

All surfaces must be clean and free of contaminants that will inhibit the cure of ELASTOSIL® Solar 2202. Examples of inhibiting contaminants are sulfur containing materials, plasticizers, urethanes, amine containing materials and organometallic compounds – especially organotin compounds. If a substrate's ability to inhibit cure is unknown, a small scale test should be run to determine compatibility.

Mixing

Component B of ELASTOSIL® Solar 2202 contains the platinum catalyst, component A the crosslinker. Even traces of the platinum catalyst may cause gelling of the component containing the crosslinker. Therefore tools (spatula, stirrers, etc.) used for handling the platinum-containing component or the catalyzed compound must not come into contact with this component. The two components should be thoroughly mixed at a 1 : 1 ratio by weight or volume.

To eliminate any air introduced during dispensing or trapped under components or devices a vacuum encapsulation is recommended.

Curing

The Curing time of addition-curing silicone rubber is highly dependent on temperature, size and heat sink properties of the components being potted.

Temperature	Curing time
23 °C	8 h
100 °C	15 min
150 °C	5 min

The reactivity can be adjusted within wide limits by adding Catalyst EP or Inhibitor PT 88 to suit the processing requirements of the particular application. While Catalyst EP increases the reactivity, i. e. pot life and curing time are reduced, inhibitor PT 88 is a pot life extender which prolongs pot life and curing time. Further information is given in our leaflet "Catalyst EP/Inhibitor PT88".

After completion of the vulcanization process the product may be continuously exposed to constantly changing climatic conditions, UV radiation and temperatures as high as 180 °C (356 °F) without damage.

Hardness

If the gel is too soft and tacky, reducing the amount of component B will result in a harder, less tacky vulcanizate. The hardest formulation is achieved with a mixing ratio for A:B of approximately 1.5:1. For logistical reasons however, we can only accept orders in a mixing ratio of A:B = 1:1.

Pigmentation

ELASTOSIL® Solar 2202 can be pigmented by adding 1 - 4 % of an ELASTOSIL® FL pigment paste.

We recommend running preliminary tests to optimize conditions for the particular application. Comprehensive processing instructions are given in our leaflet "Wacker RTV-2 Silicone Rubber-Processing".

If removal of silicone rubber from machines or dispensing equipment is necessary, white spirit or similar non-polar solvents are recommended. However, cleaning ideally should take place before the rubber is fully vulcanized. Cured silicone rubber can be removed by mechanical means, preferably in combination with a swelling agent (solvent), which will help to remove sealant residues.

Storage

ELASTOSIL® Solar 2202 should be stored between 5 and 30 °C in the tightly closed original container. The 'Best use before end' date of each batch appears on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety information

According to the latest findings, the addition-curing silicone rubber ELASTOSIL® Solar 2202 contains neither toxic nor aggressive substances which would require special handling precautions. General industrial hygiene regulations should be observed.

Detailed safety information is contained in each Material Safety Data Sheet, which can be obtained from our sales offices.

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The recommendations do not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the products for a particular purpose.

The management system has been certified according to DIN EN ISO 9001 and DIN EN ISO 14001

WACKER

and ELASTOSIL® are registered trademarks of Wacker Chemie AG.

Version 1.01 from 02-02-09 replaces
Version 1.00 from 10-11-08.

For technical, quality, or product safety questions, please contact:

Wacker Chemie AG
WACKER-SILICONES
Hanns-Seidel-Platz 4
D-81737 Munich, Germany

www.wacker.com
silicones@wacker.com